

Disclaimer: Drawings produced by DANOSA UK should be considered non-scalable and for illustrative purposes only. Issued design principals form instructions for the installation of DANOSA UK materials only and should be considered as part of an overall design rather than in isolation. Product 'Technical Datasheets' are available for all DANOSA UK products and should be consulted in conjunction with all issued DANOSA UK installation instructions. Drawings are subject to copyright and should not be reproduced without permission.

Drawing Notes:

All substrates should be primed with BITUMEN PRIMER HM. Structural substrates shown in this drawing are for illustrative purposes only.

Coverings have been removed for illustrative purposes only. DURA-DAN® systems must always be protected from UV radiation.

All POLYDAN and ESTERDAN membrane side overlaps should be a minimum of 80mm and head laps a minimum of 100mm.

Note A:
ESTERDAN 30/P ELAST AUTOADHESIVO should be bonded a minimum of 100mm onto both substrates. Where movement is likely to be more than 10mm in each plane, please speak to our technical department.

POLYDAN 180-40/P ELAST+ HM
(or POLYDAN 180-40/P ELAST+ HM GARDEN where planting exists)

DURA-DAN REINFORCEMENT MESH
(embedded in DURA-DAN ELAST 110/50 elastomeric liquid)

DURA-DAN ELAST 110/50 Elastomeric Liquid
(applied in a single application)

ESTERDAN 30/P ELAST AUTOADHESIVO
(see Note A)

Compressible Insulation
or Joint Filler Material
(as specification by others)

Maximum 10mm

Drawing Number: DUK-D-(G)-095	Revision: 00
Date Drawn: January 2019	Author: SL

Drawing Title:
Pre-Cast Panel Joint (Max 10mm)
DURA-DAN® Structural Hot Melt



Building together

DANOSA UK Limited

Tel: 0845 074 0553 | www.danosa.co.uk | uktechnical@danosa.com